

Neutralysal Premium

Version: jan-18

Neutralysal Premium is a colorless saltpeter resistant treatment. It is for curing walls that have been degraded by saltpeter. It prevents the appearance of white stain caused by absorption of water capillarity with salinity from the wall.

PRODUCT DESCRIPTION

Features:

Protects from effects of saltpeter.
Prevents the appearance of white stains.
Suitable for interiors and exteriors.
Tough and long-lasting.
Not cracking.

Technical properties:

Specific weight	1.2 ± 0.05 g/cm ³
pH	12.5 ± 1
Viscosity	< 50 U.K.
Nature	EDTA.Na ₄
Appearance	Yellowish liquid
Finish	Colourless

Yield:

7-8 m²/l (1 coat). It depends on the type and condition of the substrate. The exact consumption must be determined by the means of a sampling of the work.

Format:

Available in pots of 1 l , 5 l.

Storage:

Keep in original pack, closed and in a cool and dry place. Keep from freezing and avoid direct sun exposure. Unopened, it may be conserved for at least 36 months from the date of manufacture.

APPLICATINO INSTRUCTIONS

Application surfaces:

On the surfaces that present saltpeter due to the absorption of water by capillarity.

Conditions of the substrate:

The substrate must be dry, firm, well-adhered and free from any impurities that may hinder the product from setting fully.

Preparation of the substrate:

Clean the substrate with water to force the precipitation of encapsulated salts. Allow to dry at least 24 hours.

If the substrate presents algae, mold, fungi and / or other impurities, it is recommended to do a thorough cleaning, eliminating in its entirety and with specific products for this purpose.

If the substrate is not well adhered, first remove areas that do not adhere by scraping and brushing.

If the substrate has poor adhesion (sandy, dusty, etc.), brush and consolidate with Minerseal Premium diluted 3:1 with water.

Application method:

Mix well to ensure a even consistency and apply one coat.

Drying:

24 hours at 25 °C and 60% relative humidity.

Environmental conditions:

The work temperature (environment and support) must be between +5 °C and +32 °C. Do not apply in direct sunlight or on substrate heated by the sun.

Tools:

Roller, brush or spray gun.

Tool cleaning:

Clean tools after use with warm water.

Notes

The mineral substrate must be at least 28 days old.

The substrates to be treated must be resistant to high alkalinity.

In case of rain, let the substrate dry for at least 24 hours before applying.

It is recommended to protect the treated surface from rain until the subsequent application.

Avoid contact with aluminum, copper, copper and nickel alloys.

The parts that are not going to be treated must be protected (glass, wood, etc.).

Do not mix with other products or specific properties may change.

ADDITIONAL INFORMATION

Usage warnings:

None in particular for normal use and people who do not have special pathologies. Alkaline product, protect skin and eyes especially. Apply with good ventilation, do not inhale product. Keep out of reach of children.

Waste management:

According to local legal provisions. The pots are made of recycled polypropylene. Help protect the environment, do not throw waste through the drain and use the nearest recycling centre.

Responsible gesture:

Minimize the product waste by estimating the amount you will need. Recover the unused product to give it a new use, keep it under the Storage section.

Safety information:

For information regarding safety, physical, ecological and toxicological information see the latest version of the product's Material Safety Data Sheet.

Technical substrate:

For further information, please contact with local distributor or manufacture (technicalsupport@graphenstone.com).

The information provided is given in good faith, based on current knowledge and IEdiSA's experience with the products when they are properly stored, handled and applied in normal situations and in accordance with the recommendations of IEdiSA. The Technical Specifications sheet is useful for information and consulting but is not legally binding. In particular, it does not exempt the user from testing and verifying the suitability of the product for the desired application and purpose. IEdiSA reserves the right to modifications that improve the product or its application. This version invalidates previous ones.